



Industrial Chemicals & Resins Co. LLC.

Thermoplastic Acrylic Resin

N-535 TPA

Xylene Soluble

Delivery Form:
55% in Xylene, 180 kg (Drums)

PRINCIPAL PROPERTIES:

Low Glass Transition Temperature with high viscosity
Good physical drying
Very good Flexibility. Good Gloss and Gloss Retention
Non -yellowing
Very good exterior and interior durability

APPLICATIONS:

Non-yellowing Premium Quality Decorative Enamels
Acrylic Top Coat for textured paints
Non-yellowing Industrial Quick Drying Enamels

CHARACTERISTICS:

Type of resin	Thermoplastic Acrylic
Solid content (% by wt)	55%± 1
Solvent	Xylene
Viscosity @ 25° C (Brookfield RVT)	60 – 150 Poise
Acid value (on solids)	< 10 mg KOH
Colour Gardner	1 max (delivery form)
Clarity	Excellent

SOLUBILITY:

Aliphatic Solvents	Limited
Aromatic Solvents	Soluble
Ketones	Soluble
Esters	Soluble
Alcohols	Limited

COMPATIBILITY:

Chlorinated Plasticizers	Compatible
DOP, DBP & other Phthalates	Compatible
Chlorinated Rubber	Compatible
Alkyd Resins	Very Limited
Vinyl Resins	Compatible

B 882, Jebel Ali, Industrial Area # 2 , P.O. Box 34398, Dubai, U.A.E.
Tel. No.: +971 4 8801516 - Fax No.: +971 4 8801192